

BEST AVAILABLE COPY

(9)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

**0 292 975
A1**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 88108439.6

(51) Int. Cl.⁴: **D21D 3/00 , D21H 3/02 ,
B65D 85/80**

(22) Date of filing: 26.05.88

(30) Priority: 26.05.87 GB 8712349

(43) Date of publication of application:
30.11.88 Bulletin 88/48

(84) Designated Contracting States:
DE FR GB IT SE

(71) Applicant: **HERCULES INCORPORATED**
Hercules Plaza
Wilmington Delaware 19894(US)

(72) Inventor: **Walkden, Stephen Anthony**
29 Farmingdale Lane - Morningside
Newark, Delaware, 19711(US)

(74) Representative: **Lederer, Franz, Dr. et al**
Van der Werth, Lederer & Riederer
Patentanwälte Lucile-Grahn-Strasse 22
D-8000 München 80(DE)

(54) Sizing pulp.

(57) In a process for increasing the resistance of the cut edges of liquid-packaging board to penetration by hot hydrogen peroxide, an emulsion of an alkyl ketene dimer size, a cationic rosin size, and an insolubilizing agent, are used by adding both sizes and the insolubilizing agent either separately or in preblended form to an aqueous pulp slurry at a neutral to alkaline pH in a machine for producing the liquid-packaging board, before the board is sterilized with a hot aqueous solution of hydrogen peroxide.

EP 0 292 975 A1

SIZING PULP

The present invention relates to the sizing of pulp for use in producing liquid packaging board.

In recent years there has been a trend towards packaging liquid products, and in particular liquid dairy products such as milk and cream, in containers made out of coated paper-based board. The coating may be on one side of the board, but is generally on both sides. The coating is generally of polyethylene, although other substances are used.

In order to be able to function effectively in such a container, the board must be resistant to the effects of the liquid. For liquid dairy products, the most aggressive component of the liquid is generally lactic acid. The most vulnerable area of the board tends to be its cut edge.

Board manufacturers have therefore investigated ways to improve the resistance of board to edge penetration by lactic acid-containing liquids. It is known that board sized with a ketene dimer (KD) has good resistance to edge penetration by lactic acid-containing liquids.

More recently, there has been a trend towards aseptic packaging of consumable liquids and in particular liquid dairy products. In order to carry out aseptic packaging, it is necessary to sterilize the package as well as its contents. It has been proposed that containers made out of board should be sterilized by use of hydrogen peroxide solutions at elevated temperatures. It has been found that board sized with a KD has low resistance to edge-penetration by hot hydrogen peroxide-containing solutions. There is therefore a need for a board which has good resistance to edge penetration by such hot solutions of hydrogen peroxide, and particularly by liquids containing lactic acid following contact with hot hydrogen peroxide.

It has been shown that board sized with a cationic rosin size (CRS) or with a conventional anionic rosin size (emulsion, paste or soap) has good resistance to edge penetration by hot hydrogen peroxide-containing liquids, but low resistance to edge penetration by lactic acid-containing liquids.

It is well known in the art that sizing with KD'S must be carried out at neutral or slightly alkaline pH's (because 7 and 8.5) in order to achieve effective sizing. Moreover, sizing with KD's can be adversely affected by the presence of some cations, such as aluminum cations.

It is also well known in the art that, in order to be effective, sizing with CRS must be carried out at acidic pH's between 4 and 6, and sizing with conventional rosin sizes must be carried out at acidic pH's between 4 and 5. Further, both sizes require the presence of an insolubilizing agent (i.e. a compound which forms an insoluble complex or salt with the size). The most commonly used insolubilizing agent is alum (A12(SO4)3).

US-A-4 522 686 discloses a sizing composition in the form of an aqueous dispersion containing a hydrophobic cellulose reactive sizing agent, such as a KD, fortified rosin and a water-soluble, nitrogen containing cationic dispersing agent, the last two components forming the elements of a CRS. As shown in the Examples of this patent, the dispersion is made by producing a KD emulsion using a cationic resin. A cationic emulsion of fortified rosin is then also prepared. The final dispersion is made by mixing the two emulsions in various ratios. The final dispersion is then used, with or without the addition of alum, to produce sized paper from a pulp at a pH of about 6.5. The patent shows that using such a cationic dispersion results in improved sizing, measured using the Hercules Size Test solution No. 2 to 80% reflectance. This measures the surface sizing of the paper. However, there is no suggestion that there is a particular problem caused by sterilization by hydrogen peroxide, nor is there any indication that the sizing using the combined cationic dispersion has any effect on resistance to edge penetration by hydrogen peroxide-containing liquids nor by liquids containing lactic acid following contact with hot hydrogen peroxide solutions.

There is no known correlation between surface sizing and edge penetration resistance - good surface sizing does not ensure good edge penetration resistance. Further the measurement of effects of aggressive liquids such as hot hydrogen peroxide-containing liquids and lactic acid can give very different results depending on the tests used for such measurements.

In fact, as shown by the introduction to the said U.S. patent, the object of the invention is not only to improve sizing per se but to overcome several of the well-known disadvantages associated with either the cellulose reactive sizing agent or the cationic rosin size alone, and particularly, to improve the rate at which sizing develops. If sizing develops quickly, newly-formed paper is able to run more quickly through the machine, and in particular through the sizing press, which is clearly advantageous from an operational viewpoint for the production of paper, but has no relevance to the production of paper board in the absence of a sizing press, and its properties in use.

It has surprisingly been found that if a KD and a CRS are added, together with an insolubilizing agent,

to a pulp slurry at neutral to alkaline pH and the pulp is then formed into board, the board has good resistance to edge penetration by both hydrogen peroxide- and lactic acid-containing liquids.

According to the invention, an emulsion of an alkyl ketene dimer size in conjunction with a cationic rosin size and an insolubilizing agent is used for increasing the resistance of the cut edges of liquid-packaging board to penetration by hot hydrogen peroxide by adding both sizes and the insolubilizing agent either
5 separately or in preblended form to the aqueous pulp slurry at a neutral to alkaline pH in a machine for producing the liquid-packaging board.

Moreover, it has been found that the resistance of the boards in both respects is unexpectedly better than would be predicted by adding together the effects of the two sizes when used separately.

10 Although it is preferred to add the components separately, the same surprising results are given by preblending the KD and the CRS before addition to the pulp slurry.

This surprising effect is even more unexpected since it was found that the use of a KD and an anionic rosin size did not give the same sizing effects. This combination gives good resistance to edge penetration by hot hydrogen peroxide but has an adverse effect on edge penetration by lactic acid.

15 In the absence of preblending, which is not preferred, the KD, the CRS and the insolubilizing agent may be added separately but simultaneously to the pulp slurry, advantageously immediately before the slurry is fed to a board-forming machine. However, the components may alternatively be added sequentially and in any desired order. The order of addition of the KD and the CRS is not critical. It is only necessary to ensure that the pulp remains in an aqueous environment at neutral to alkaline pH at all times between the addition
20 of the two sizing agents.


Preferably, the CRS and insolubilizing agent are added to the vessel in which the slurry is initially formed and the KD is added immediately before the slurry is fed to the forming machine.

Advantageously, the CRS and the insolubilizing agent are mixed together prior to the mixture being added to the slurry. However, the insolubilizing agent may be added separately at any stage during the
25 processing of the slurry either before or after the addition of the CRS.

It is envisaged that the pulp, once treated with the three components, will be formed into board for use in aseptic packaging of liquids. However, the invention is not limited to such use, and the pulp may be formed into any desired product. Any conventional forming machine may be used.

Any of the KD's known in the art may be used in the process of the present invention at the levels
30 generally used in sizing. For instance, the final pulp slurry may contain from 0.010 to 0.6% KD (based on the dry weight of the pulp (db)). Preferably, the final slurry contains about 0.12% db of KD.

Ketene dimers used as sizing agents are dimers having the formula:



where R is a hydrocarbon radical, such as alkyl having at least 8 carbon atoms, cycloalkyl having at least 6
35 carbon atoms, aryl, aralkyl and alkaryl. In naming ketene dimers, the radical "R" is named followed by "ketene dimer". Thus decyl ketene dimer is $[C_{10}H_{21}-CH=C=O]_2$. Examples of ketene dimers include octyl, decyl, dodecyl, tetradecyl, hexadecyl, octadecyl, eicosyl, docosyl, tetracosyl, phenyl, benzyl, beta-naphthyl and cyclohexyl ketene dimers and the ketene dimers prepared by known methods from organic acids such as montanic acid, naphthenic acid, $\Delta 9,10$ -decylenic acid, $\Delta 9,10$ -dodecylenic acid, palmitoleic
40 acid, oleic acid, ricinoleic acid, linoleic acid, and eleostearic acid, and from naturally occurring mixtures of fatty acids, such as those mixtures found in coconut oil, babassu oil, palm kernel oil, palm oil, olive oil, peanut oil, rape oil, beef tallow, lard (leaf) and whale blubber. Mixtures of any of the above-named fatty acids with each other may also be used.

Any of the CRS's known in the art may be used in the process of the present invention at the levels
45 generally used in sizing. For instance, the final pulp slurry may contain from 0.4 to 4.0% db of an alum-containing CRS. Preferably, the final slurry contains about 1% of an alum-containing CRS.

A preferred type of CRS is a fortified rosin in a liquid cationic dispersing agent. CRS's of this type are disclosed in US-A-3 817 768, US-A-3 966 654 and US-A-4 199 369.

The insolubilizing agent may be any one of those known in the art, and is preferably alum. The amount
50 used is preferably substantially the same as that normally used with CRS's. Generally, the amount of insolubilizing agent used will be from 0.5 to 2.0, preferably from 1 to 1.5, parts per part of the rosin component.

The pulp slurry may be processed in any conventional manner before the pulp is formed, for instance into a board for aseptic packaging use, and any other conventional additives, such as flocculating agents,
55 pigments and fillers, may be added as desired.

The present invention also includes products, such as boards, made from pulp treated by the process of the present invention.

The following examples are given for the purpose of illustrating the present invention. All parts and

percentages are by weight unless otherwise indicated.

A number of samples of paper-based board for use in aseptic packaging of dairy products were prepared. The original pulp was formed into a slurry and treated in a conventional system before being fed to a conventional board forming machine.

Two grades of starting pulp were used, one being a woodfree pulp (WP) comprising 50% Lumi bleached softwood sulphate (25° SR) and 50% Oulu beached hardwood sulphate (25° SR). The second grade had added high yield pulp (+HYP) and comprised 40% Lumi (as above), 40% Oulu (as above) and 20% Rockhammer high yield pulp.

The pulp slurry was initially adjusted to a desired pH and then the sizing agents added immediately prior to feeding the treated slurry to the forming machine.

Once the board had been formed it was subject to the following tests.

1. Cobb Test. - 1 minute water Cobb test, to test for surface sizing. The results are given as grams of water absorbed per square meter (g/m²).

2. 24h lactic edge penetration. - Samples of board were laminated on both sides with a polyester film using a hot melt adhesive. 50 x 50 mm samples were immersed in a 1% solution of lactic acid at 23° C for 24 hours. After immersion the samples were removed, dried by blotting and reweighed. The results are given as grams of solution absorbed per meter of raw edge (g/m).

3. 10 min lactic edge penetration. - The test procedure was as for Test 2 above, except that self-adhesive tape was used instead of polyester film, the solution comprised 1% lactic acid held at 70° C, and the immersion time was 10 minutes.

4. 10 min peroxide edge penetration. - The test procedure was as for Test 3 above, except that the solution comprised 30% hydrogen peroxide at 80° C.

It will be appreciated that in all these tests good sizing will give a lower value than poor sizing. For the Cobb test, good sizing values are about 20 and poor sizing values are in excess of 40.

The conditions and additives used to produce the boards are given in Table I and the results of the tests are given in Table II below. The tests include both control experiments and examples of the invention. In Table I the amounts of additives used are given as % db.

The ketene dimer (KD) was Aquapel® 360X, an alkyl ketene dimer having a mixture of C14 and C16 alkyl chains in an emulsion containing a cationic potato starch derivative, sold by Hercules Limited.

The cationic rosin size contained fortified rosin, an aluminum compound (alum) and a polyamide wet strength resin, and was sold by Hercules Limited. The amount of alum present comprises 1.0 part per part of the rosin component.

TABLE I

TESTS	SLURRY pH	KD	CRS +ALUM	PULP
A	4.5		1	WF (CRS or anionic size)
B	7.5	-	1	WF
C	7.5	0.12	-	WF
D	7.5	0.12	1	WF
E	7.5	0.12	-	+HYP
F	7.5	-	1	+HYP
G	7.5	0.12	1	+HYP

TABLE II

Test Results

TESTS	1	2	3	4
A	23.5	3.08	0.50	0.27
B	41.8	1.73	2.78	1.24
C	17.0	0.32	1.32	0.41
D(Example)	18.3	0.33	0.52	0.22
E	19.6	0.48	0.17	1.32
F	*	2.06	2.34	2.78
G(Example)	19.2	0.50	0.25	0.52

* indicates that water penetrated the sample during testing.

It can be seen from Test A that board sized with either CRS or anionic rosin size at acid pH has low lactic acid resistance, but high peroxide resistance. However, when CRS is applied at neutral pH, it provides no useful sizing or penetration resistance (see Tests B and F).

Tests C and E show that sizing with KD at neutral pH provides good lactic resistance by low peroxide resistance.

Tests D and G, which are Examples of the invention, show that sizing with KD and CRS provides not only good lactic and peroxide resistance, which is in itself unexpected, but also better results than could be expected from a consideration of the results for the two components used alone. It is to be noted that for WF pulps, the peroxide resistance for Example D is better than any of the others. Moreover, in all cases, the 24h lactic and 10 min lactic test results are equivalent to those obtained for the separate components. It is surprising that such good results can be obtained from a system which would be expected to have compatibility problems.

A further series of trials was carried out on a pilot paper machine using the slightly different pulp furnish as follow:

- 40% Rockhammer CTMP
- 30% Mado Kraft
- 30% Oulu birch

All chemical additions were made to the mixing box i.e. after the machine refiner but before the Formar. Where "separate" addition of alum is shown, then both size and alum were added as dilute emulsions via a funnel.

Table III shows that four different anionic sizes gave the same results, namely:

- All improved the hot peroxide edge resistance but not as efficiently as the CRS.
- All has an adverse effect on cold lactic acid edge resistance.

Table IV shows the effect of the following CRS's: -

- A CRS containing alum as described under Table I.
- A CRS containing alum but with a different liquid cationic dispersing agent than above.
- A CRS not containing alum - alum was added separately.
- A CRS containing alum blended with Aquapel® 360X.
- A CRS not containing alum blended with Aquapel® 360X and alum added.

Table IV shows that all cationic sizes had either no effect or a slightly beneficial effect on lactic acid edge resistance and that they all had a beneficial effect on hot hydrogen peroxide edge resistance.

Table V shows the results obtained with two different Hercules anionic sizes added separately from KD, mixed with KD, and mixed with KD and alum. The results show that all combinations with anionic rosin size had adverse effects on col lactic acid edge resistance and gave variable results on hot hydrogen peroxide edge resistance but all were inferior to the CRS.

It will be appreciated that the invention has been described above purely by way of illustration and that modifications of detail can be made within the scope of the invention. For instance, the KD may be dispersed in a liquid cationic dispersing agent with a composition that is well known in the paper industry. Alternatively, the KD may be dispersed directly in the CRS to make a composition useful in this invention.

TABLE III

Example	RO Size ϕ	Resin size ϕ	Alum ϕ	Raw edge penetration 24 hr. Lactic	Raw edge penetration 10 min. H ₂ O, @ 70°C	Ortho naturally aged	Sheet weight g/m ²
C-6	0.125	—	—	0.96	1.74	24.3	162.3
3	0.125	Marcelles CSF contain- ing alum (1)	—	0.90	0.33	21.5	162.7
C-7	0.125	Marcelles anionic s.s. (1)	0.52	1.33	0.45	21.4	166.0
C-8	0.125	Competitive anionic size (1)	0.52	1.24	0.54	22.6	165.3
C-9	0.125	Competitive anionic size (1)	0.52	1.22	0.30	21.7	166.4
C-10	0.125	Competitive anionic size (1)	0.52	1.35	0.42	21.3	164.9

(1) Cationic resin size used in Examples 1 and 2

(2) MARCELLES (3) anionic resin size containing fortified resin stabilized with casein, sold by Marcelles Incorporated.

(4) MARCEL 443 anionic resin size containing fortified resin stabilized with casein, sold by Tennessee Inc.

(5) MARCEL 440 anionic resin size containing fortified resin stabilized with casein, sold by Marahl GmbH.

(6) MARCEL 442 anionic resin size containing fortified resin stabilized with casein, sold by Maro Spa.

TABLE IV

Example	RD Size ϕ	Resin size ϕ	Alum ϕ	Pen edge penetration 24 hr. Lactic	Pen edge penetration 10 min. H ₂ O ₂ @ 70°C	Obb naturally aged	Sheet weight g/m ²
C-11	0.122	--	--	1.54	3.42	22.2	168.6
4	0.122	Hercules CBS contain- ing alum (1)	--	1.10	0.45	22.3	171.8
5	0.122	Hercules CBS contain- ing alum (1)	--	1.54	0.61	19.7	170.1
6	0.122	Hercules CBS (1)	0.52	1.44	0.61	19.8	169.9
7	[0.122]	Hercules CBS contain- ing alum (1)	--	1.16	0.44	20.4	167.3
8	{0.122}	Hercules CBS (1)	0.52	1.27	0.56	20.3	167.5

(*) Brackets () denote preblending of the components before addition.

(1) Cationic resin size containing fortified resin size stabilized with a cationic resin based on WMR (CBS contains one part alum per part of resin).

(1) Cationic resin size used in Examples 1 and 2 but without alum.

TABLE V

Formula	MD size ϕ	Resin size ϕ	Alum ϕ	Edge penetration		Cobb naturally aged	Sheet weight g/m ²
				24 hr. Lactic	10 min. H ₂ O @ 70°C		
C-11	0.125	—	—	0.86	2.40	24.5	164.0
C-13	0.125	Marcales anionic size (1)	0.5	1.35	0.44	22.4	164.5
C-14	[0.125]	Marcales anionic size (1)	0.5	2.97	3.13	28.0	164.6
C-15	[0.125]	Marcales anionic size (1)	0.52	2.67	2.89	23.2	165.8
C-16	0.125	Marcales anionic size (1)	0.5	1.45	0.56	21.4	166.0
C-17	[0.125]	Marcales anionic size (1)	0.52	1.82	0.67	23.9	164.5
C-18	[0.125]	Marcales anionic size (1)	0.52	2.65	1.83	22.4	165.5
9	0.12	Marcales CMB containing alum (1)	—	0.79	0.29	20.6	164.0

(*) Brackets () denote preblending of the components before addition.
Combinations containing anionic resin size and alum were unstable.

(**) T Lin 7635 anionic resin size containing fortified resin size stabilized with synthetic surfactant.

Claims

5

1. Use of an emulsion of an alkyl ketene dimer size in conjunction with a cationic rosin size and an insolubilizing agent, for increasing the resistance of the cut edges of liquid-packaging board to penetration by hot hydrogen peroxide by adding both sizes and the insolubilizing agent either separately or in preblended form to the aqueous pulp slurry at a neutral to alkaline pH in a machine for producing the liquid-packaging board.

10

2. Use of an emulsion of an alkyl ketene dimer in conjunction with a cationic rosin size and an insolubilizing agent as claimed in claim 1, characterized in that the insolubilizing agent is alum.

15

3. Use of an emulsion of an alkyl ketene dimer in conjunction with a cationic rosin size and an insolubilizing agent as claimed in claim 1 or 2, characterized in that the cationic rosin size and the insolubilizing agent are added to the vessel in which the slurry is initially formed and the ketene dimer size is added immediately before the slurry is fed to the board-forming machine.

4. Use of an emulsion of an alkyl ketene dimer in conjunction with a cationic rosin size and an insolubilizing agent as claimed in claim 1, 2, or 3, characterized in that the use includes filling the container with a lactic acid-containing liquid.

20

5. A process for making a container for consumable liquids including the steps of forming paper board from a pulp slurry at neutral to alkaline pH, cutting the board to unit packaging size and thereby exposing cut edges of the board, coating the board with polyethylene, and treating it with a hot aqueous solution of hydrogen peroxide, characterized in that an emulsion of an alkyl ketene dimer size, a cationic rosin size, and an insolubilizing agent are added to the pulp before the forming step.

25

6. A process for making a container for consumable liquids as claimed in claim 5, further characterized in that the cationic rosin size and the insolubilizing agent are added to the vessel in which the slurry is initially formed and the ketene dimer size is added immediately before the slurry is fed to the board-forming machine.

7. A process for making a container for consumable liquids as claimed in claim 4, further characterized in that the container is designed to be filled with a lactic acid-containing liquid.

30

35

40

45

50

55



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 88 10 8439

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
D,A	US-A-4 522 686 (D.H. DUMAS) * Whole document * ---	1,2,5	D 21 D 3/00 D 21 H 3/02 B 65 D 85/80
A	DE-A-3 035 634 (FELDMÜHLE) * Claims 1,2,5-7; examples 2,3 * ---	1-3,5,6	
A	EP-A-0 208 667 (CASCO NOBEL) * Abstract; column 3, line 37 - column 4, line 48; column 8, line 55 - column 10, line 2; examples 6-9 * ---	1,2,4,5,7	
D,A	US-A-3 966 654 (P.H. ALDRICH) ---		
E	EP-A-0 275 851 (CASCO NOBEL) * Abstract; page 3, paragraph 3; examples 6-10 * -----	1,4,5,7	
			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
			B 65 D D 21 D D 21 H
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 07-09-1988	Examiner NESTBY K.
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.